

Skid Grip Anti-Slip Coating - F065 Series

Product Description

Skid-Grip is an outstanding 100% acrylic-textured coating for use over asphalt, concrete or other surfaces, where an extremely durable, skid resistant finish is desired. Skid-Grip is an excellent choice as a Traffic Marking Coating, to be used on sidewalks, curbs, and crosswalks. Skid-Grip exceeds ADA standards for anti-slip surfaces.

Recommended Use

Patios, pool decks, tennis courts, basketball courts, curbs, sidewalks, crosswalks, driveways, steps, walkways, ramps. Areas where an anti-slip surface is required.

General Surface Preparation

Skid Grip must be applied to a properly prepared sound surface. Surfaces must be thoroughly cleaned of all dirt and dust. Dirty surfaces should be washed with a strong detergent solution, rinsed with clean water and allowed to dry overnight. Grease, oils and wax should be removed by solvent cleaning to insure proper adhesion of the finish paint. All old, loose, scaly or flaking paint must be removed back to a sound substrate before any repainting is attempted. New concrete should be allowed to cure a minimum of 30 days before applying any finish. Steel troweled, hard, glassy smooth, and sealed concrete (curing agents or sealers) should be mechanically abraded or acid etched to create a profile to obtain proper adhesion. Water droplets should immediately penetrate into concrete to determine if coating is possible.

Note: To ensure proper surface preparation refer to SSPC-SP13/NACE

Application

FixAll Skid Grip can be applied by brush or roller. Apply 2 coats for proper performance. Continue to work with a wet edge, to retain uniformity of finish. For larger surfaces FixAll Skid Grip is best applied by pouring from container in an "S" pattern and then spreading with a squeegee or 18" roller. Apply liberally, recommended Wet Film Thickness is 16 mils. For best results, apply with a 1/2" to 1 1/4" Roller Nap

Clean up

A mixture of warm water and mild soap is the best cleaning solution for water-based paints. Prepare soapy water and pour into a clean container. Dip the paint brush into the mixture, working the soap through the brush bristles. Follow with a clear water rinse. Repeat the process if necessary. Always use a clean container with clean soapy water and follow with a clear water rinse. For stubborn water-based paints, try mineral spirits or lacquer thinner, followed by warm soapy water and a clear water rinse.

Architectural Specifications

Asphalt, concrete other surfaces:

2 coats FixAll Skid-Grip Anti-Slip Paint F065XX on properly prepared surface.

New wood:

1 coat California Paints Troubleshooter Fast Drying Alkyd Primer 227XX on properly prepared wood

2 coats of FixAll Skid-Grip Anti-Slip Paint F065XX

Precautions

Do not apply when air and surface temperature are below 50° F (10° C). Do not apply when rain is imminent. Do not apply when surface is above 95° F (35° C). Do not apply over tar emulsions less than 4 years old. Pool decks must be clean and dry. Do not put in service until 24 hours after the last coat. Light foot traffic 16-24 hours. Heavy foot traffic 24-48 hours.

Environmental Health and Safety Information

Keep out of reach of children. Do not take internally. Close container after each use.

Protect from freezing.

Skid Grip Anti-Slip Coating - F065 Series

*Depending upon color choice, non zero VOC colorant added to this product may significantly increase VOC levels.

WARNING: This product contains a chemical known to the State of California to cause cancer, birth defects or other reproductive harm.

Lead Warning ! - If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

Some paint products may contain chemicals which are harmful if they come in contact with exposed skin. Protection for exposed skin (gloves, protective creams) should be available, and used per product directions.

CAUTION: All floor enamels are more slippery when the surface becomes wet or contaminated by dirt, oils, food or beverage residues, or other debris. To help reduce the possibility of slipping on a dry, clean floor, add an anti-slip additive to product before application. To attain the best possible skid resistance, coated areas must be kept dry, properly cleaned and maintained.

USE COMPLETELY OR DISPOSE OF PROPERLY: Dispose of in accordance with applicable Federal, State and Local regulations. Under the Resource Conservation and Recovery Act (RCRA) regulations, it is the responsibility of the product user to determine, at the time of disposal, whether a material should be classified as a hazardous waste. For recycling guidance of any unused amount, contact your local or provincial organization of recovery and recycling. Dry, empty containers may be recycled in a can recycling program where facilities are available and sanctioned by local authorities.

Notes

PLEASE NOTE: all concrete surfaces must be profiled or etched prior to coating. The surface must be allowed to readily absorb water and should have the feel of 180 grit sandpaper.

Technical Data

Product Type	Specialty
Exposure	Interior/ Exterior
Specular Gloss	5° ± 2
Volume Solids	54.3% ± 2
Weight Solids	70.0% ± 2
Vehicle Solids	80.1% ± 2
Pigment	19.9% ± 2
Wet Film Thickness	16 mils
Dry Film Thickness	9 mils
Viscosity @ 77 °F	85KU ± 5
Max VOC	100 g/l
Flash Point ° F	Non-Combustible
Thinner	Water
Clean - up	Soap & Water

Surface Spread Rate

Smooth	80-100 s.f./gal.
Porous	60-80 s.f./gal.

(Spray Application is 50% of above)

Drying Times

To Touch	4 hours
To Handle	18 hours
To Recoat	12 hours
To Wash	14 days

(@ 70 - 77 °F, 50% R.H)

Surface Temperature At Application

Minimum: Over 50°F	Maximum: Under 90°F
--------------------	---------------------

Storage Temperature

Store Between Over 40°F to Under 100°F

Tools & Equipments

Brush	Synthetic, Nylon or Polyester
Roller	1/2" - 1 1/4" synthetic
Airless Spray	Not Recommended

Available Package Sizes

5 Gallon	Gallon
(Weight Per Gallon: 12.7 lbs. ± .5 lb)	

Available Colors and Bases

Accent Base	Tintable White
-------------	----------------

Available in 8 stock colors